



DULUX SOLARSCREEN EXTERIOR TRANSPARENT WOOD FINISH

A339-LINE (SOLVENTBASED)

PRODUCT INFORMATION

| | |
|---------------------|---|
| PRODUCT NAME | Dulux Solarscreen Exterior Transparent Wood Finish |
| Product Code | A339-Line |
| DESCRIPTION | Dulux Solarscreen Exterior Transparent Wood Finish is a durable pigmented varnish based on a special resin for protection and decoration purposes. |
| USAGE | Suitable for use on all types of new or previously painted wood surfaces. |
| BENEFITS | Excellent abrasion resistance. Highlights the natural beauty of the grain of the wood. Water resistant, flexible and will provide long lasting protection. Its unique formulation will filter out UV rays thereby minimizing the traditional problems of cracking, flaking and peeling. |
| PACK SIZE | 1 and 5 litres. |
| COLOR RANGE | Refer to Colour Inspirations. |

PERFORMANCE GUIDE

| | |
|-----------------------------|--|
| FILM PROPERTIES | |
| Chemical Resistance | Resists alcohols and aliphatic hydrocarbon. Film is liable to attack from other strong solvents. |
| Heat Resistance | Resistant up to 90°C. |
| Water Resistance | Resistant to the atmospheric humidity and rain normally experienced in exterior environments. |
| THEORETICAL COVERAGE | A guide to the theoretical coverage which can be achieved under normal conditions is 19 m ² /L. |

PRODUCT DATA

| | |
|------------------------------|---|
| COMPOSITION (nominal) | Pigment : Lightfast Non Lead Pigments. Binder : Modified Alkyd. Solvent : White Spirit. |
| VOLUME SOLIDS | 38% (nominal). |
| FLASH POINT | 32-55 °C. |

APPLICATION

| | |
|-----------------------|--|
| THINNING | |
| Brush | For sealing new or bare surfaces thin up to 1 part of Dulux Thinner 850-41 or white spirit to 5 parts of paint (20%). For normal use thinning is usually not necessary. |
| DRYING TIMES | Single coat at standard thickness: |
| Touch Dry | 1-2 hours. |
| Recoat | 4 hours. |
| CLEANING UP | Clean all equipment with Dulux Thinner 850-41 or white spirit immediately after use. |
| FILM THICKNESS | Wet : 50 micro-metres. Dry : 20 micro-metres. |

PRE-APPLICATION

| | | |
|----------------------------|---|---|
| SURFACE PREPARATION | Surfaces must be clean, dry, free from all defective or poorly adhering material, dirt, grease, wax etc. All surfaces should be thoroughly rubbed down in the direction of the grain, using a suitable abrasive paper and then dusted off. It should not be applied on areas where moisture reading (as measured by Protimeter) exceeds 17%. These substrate should be left to dry further. | |
| SYSTEM INFORMATION | PRIMER N/A | FINISH (3 COATS) Dulux Solarscreen Exterior Transparent Wood Finish (A339) |

PRECAUTION

| | |
|---|--|
| HEALTH, SAFETY AND ENVIRONMENT INFORMATION | FLAMMABLE <ul style="list-style-type: none">• Toxic to aquatic organisms may cause long-term adverse side effects in the aquatic environment.• Repeated exposure may cause skin dryness or cracking.• Avoid contact with skin.• Contains: ETHYL METHYL KETOXIME, COBALT CARBOXYLATE, BIS (1,2,2,6,6-PENTAMETHYL-4-PIPERIDYL) SEBACATE. May produce an allergic reaction.• In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.• In case of contact with skin, wash immediately with soap and water or a proprietary cleanser.• Do not use solvents or thinners.• Keep away from food, drinks, animal feed and out of reach of children.• Keep away from combustible material.• Container must be stored in a cool and shaded place.• It must be tightly closed in a secure, upright position.• Work in a well-ventilated area and do not breathe in vapor or spray.• A suitable mask should be worn during sanding.• Wear eye/hand protection.• In case of fire use foam, dry powder, AFFF, CO2-Never use water.• In case of spillage, contain and collect spillage using sand or earth and do not empty into water courses, drains or environment.• Dispose of any paint waste in accordance with the appropriate Environmental Quality Regulations.• Refer to Dulux Product Safety Data Sheet for further details.• In case of emergency, refer to Emergency Incident Response Hotline 1-800-80-6187 |
|---|--|

Any advice, recommendations, information, assistance or service provided by Akzo Nobel Paints in relation to goods manufactured or marketed by it or their use or any application is given in good faith. However, any advice, recommendations, information, assistance or service provided by Akzo Nobel Paints is provided without expressed or implied warranties.

Akzo Nobel Paints (Malaysia) Sdn Bhd

(Formerly known as ICI Paints (Malaysia) Sdn Bhd)

For further details on Product Data Sheet, kindly contact:

Customer Care Department

Tel: 1-800-88-9338 Website: www.dulux.com.my Email: customercare.my@akzonobel.com

A BRAND FROM
AkzoNobel